

GRAPHICS - INK-JET DIGITAL

Issue date : 24/02/2014  
Date last modification : 12/04/2018**4-GL3B-08460 RI-JET 75 OPTIMA GLOSS WHITE AP940 PERMANENT WKPE140 AIRFLOW N****Face Material**

Gloss white polymeric soft vinyl.

Type	Polymeric vinyl		
Colour and Finish	Gloss white		
Weight	100 g/m <sup>2</sup> ±10%	ISO-536	
Thickness	75 µ ±10%	ISO 534-80	

**Adhesive**

Acrylic permanent adhesive featuring high clarity and very high cohesion. Designed for a wide variety of substrates such as glass, ABS, PS, PVC. Unsuitable for apolar surfaces (like PE and PP).

Reference	AP940 permanent		
Type	Acrylic permanent		
Min. Appl. Temp.	+10°C		
Service Temp.	-30°C/+120°C		
Shear	Very High		
Tack	6 N/25mm	FINAT FTM9	
Final Adhesion	11 N/25mm	FINAT FTM2	

**Liner**

Type	Embossed PE coated kraft paper - Airflow texture		
Colour and Finish	White		
Weight	140 g/m <sup>2</sup> ±10%	PP-032 - ISO 536	
Thickness	150 µ ±10%	ISO 534	
Transparency	n.a. %	DIN 53 147-64	

**Applications**

Solvent and eco-solvent ink-jet printing. The RI-JET series of ink jet print media give excellent print results with UV ink-jet printing. Testing for suitability between media, printers and inks is always recommended prior to use.

**Printing Methods**

The RI-JET series of ink-jet print media gives excellent print results with UV, solvent and eco-solvent ink-jet printing. Testing for suitability between media, printers and inks is always recommended prior to use.

**Shelf life**

24 months, applicable only to the material delivered by Ritrama which has not undergone further processing, under the following **STORAGE CONDITIONS**:

- This material must be stored at a temperature of 22°C ± 2°C and 50 ± 5% of Relative Humidity.
- Storage area must be dry and clean.
- Keep the material in the original packaging when not used in order to protect it from dust and contamination.
- Do not expose to direct sunlight or heat sources.

All Ritrama products are subject to strict manufacturing controls to guarantee good quality products. The above information is based on research believed to be reliable, but does not constitute a warranty. All material should be tested by the purchaser to determine suitability of the product for their purposes. All information is subject to change without prior notice.

