

ROLL LABEL - Polypropylenes

Issue date : 05/01/2005
Date last modification : 26/02/2019**4-RL2D-03491 RI-704/60 PP GLOSS CLEAR TC8 AP901 WG74****Face Material**

Gloss clear top coated polypropylene.

Type	Top coated polypropylene	
Colour and Finish	Gloss clear	
Weight	53 g/m ² ±10%	ISO-536
Thickness	58 μ ±10%	ISO 534-80

Adhesive

Acrylic permanent adhesive featuring high clarity and cohesion with strong adhesion to apolar substrates (like PE and PP).

Reference	AP901	
Type	Acrylic permanent	
Min. Appl. Temp.	-5°C	
Service Temp.	-40°C/+120°C	
Shear	High	
Tack	8 N/25mm	FINAT FTM9
Final Adhesion	7 N/25mm	FINAT FTM2

This adhesive is approved by ISEGA (Direct contact dry & moist, non fatty foodstuffs) according to the German Recommendations XIV and complies with FDA 175.105.

Liner

Type	One side siliconised Glassine	
Colour and Finish	White	
Weight	72 g/m ² ±10%	PP-032 - ISO 536
Thickness	63 μ ±10%	ISO 534
Transparency	>40 %	DIN 53 147-64

Applications

For high-end applications on rigid or semi-rigid polyethylene and polypropylene containers. Top coating and adhesive are fully compliant with food industry requirements.

Not recommended for fan folder tags.

Printing Methods

Printable with flexo UV, offset UV, letterpress UV, screenprinting UV, gravure and hot stamping. It is recommended to overvarnish in order to improve the scratch and chemical resistance of the finished label. Testing for suitability between media, printers and inks is always recommended prior to use.

Shelf life24 months, applicable only to the material delivered by Ritrama which has not undergone further processing, under the following **STORAGE CONDITIONS**:

- This material must be stored at a temperature of 22°C ± 2°C and 50 ± 5% of Relative Humidity.
- Storage area must be dry and clean.
- Keep the material in the original packaging when not used in order to protect it from dust and contamination.
- Do not expose to direct sunlight or heat sources.

All Ritrama products are subject to strict manufacturing controls to guarantee good quality products. The above information is based on research believed to be reliable, but does not constitute a warranty. All material should be tested by the purchaser to determine suitability of the product for their purposes. All information is subject to change without prior notice.

