

ROLL LABEL - COMMODITY

Issue date : 20/09/2006
Date last modification : 09/12/2016**4-RL2D-03464 RI-757/40 PP CAVITATED GLOSS WHITE TC8 AP901 WG62****Face Material**

Gloss white top coated cavitated polypropylene.

Type	Top coated cavitated polypropylene	
Colour and Finish	Gloss white	
Weight	33 g/m ² ±10%	ISO-536
Thickness	40 µ ±10%	ISO 534-80

Adhesive

Acrylic permanent adhesive featuring high clarity and cohesion with strong adhesion to apolar substrates (like PE and PP).

Reference	AP901	
Type	Acrylic permanent	
Min. Appl. Temp.	-5°C	
Service Temp.	-40°C/+120°C	
Shear	High	
Tack	8 N/25mm	FINAT FTM9
Final Adhesion	7 N/25mm	FINAT FTM2

This adhesive is approved by ISEGA (Direct contact dry & moist, non fatty foodstuffs) according to the German Recommendations XIV and complies with FDA 175.105.

Liner

Type	One side siliconised Glassine	
Colour and Finish	White	
Weight	62 g/m ² ±10%	PP-032 - ISO 536
Thickness	54 µ ±10%	ISO 534
Transparency	>45 %	DIN 53 147-64

Applications

Pearlescent finish labels, ideal for the cosmetics industry. Top coating and adhesive are fully compliant with food industry requirements. Not recommended for fan folder tags.

Printing Methods

Printable with UV flexo, UV offset, UV letterpress, UV screenprinting, gravure and hot stamping. It is recommended to overvarnish in order to improve the scratch and chemical resistance of the finished label. Testing for suitability between media, printers and inks is always recommended prior to use.

Shelf life24 months, applicable only to the material delivered by Ritrama which has not undergone further processing, under the following **STORAGE CONDITIONS**:

- This material must be stored at a temperature of 22°C ± 2°C and 50 ± 5% of Relative Humidity.
- Storage area must be dry and clean.
- Keep the material in the original packaging when not used in order to protect it from dust and contamination.
- Do not expose to direct sunlight or heat sources.

All Ritrama products are subject to strict manufacturing controls to guarantee good quality products. The above information is based on research believed to be reliable, but does not constitute a warranty. All material should be tested by the purchaser to determine suitability of the product for their purposes. All information is subject to change without prior notice.

