

ROLL LABEL - PERSONAL CARE

Issue date : 12/07/2013
Date last modification : 10/09/2018**4-RL2L-07993 GLOBALFLEX CRYSTAL AP901 PET23****Face Material**

Gloss clear squeezable bi-oriented coex polyolefin film.

Type	Polyolefin film	
Colour and Finish	Gloss clear	
Weight	47 g/m ² ±10%	ISO-536
Thickness	52 μ ±10%	ISO 534-80

Adhesive

Acrylic permanent adhesive featuring high clarity and cohesion with strong adhesion to apolar substrates (like PE and PP).

Reference	AP901	
Type	Acrylic permanent	
Min. Appl. Temp.	-5°C	
Service Temp.	-40°C/+120°C	
Shear	High	
Tack	8 N/25mm	FINAT FTM9
Final Adhesion	7 N/25mm	FINAT FTM2

This adhesive is approved by ISEGA (Direct contact dry & moist, non fatty foodstuffs) according to the German Recommendations XIV and complies with FDA 175.105.

Liner

Type	One side siliconised polyester	
Colour and Finish	Clear	
Weight	32 g/m ² ±10%	PP-032 - ISO 536
Thickness	23 μ ±10%	ISO 534
Transparency	>95 %	DIN 53 147-64

Applications

Highest quality and versatile solution for any new label application on contoured or squeezable containers. The PET liner gives good clarity to the adhesive. The liner allows very good dispensability at high speeds. Not recommended for fan folder tags.

Printing Methods

The material must be corona treated for the printability. Printable with UV letterpress, UV screenprinting, flexo UV, gravure and hot stamping.

Testing for suitability between media, printers and inks is always recommended prior to use.

Shelf life24 months, applicable only to the material delivered by Ritrama which has not undergone further processing, under the following **STORAGE CONDITIONS**:

- This material must be stored at a temperature of 22°C ± 2°C and 50 ± 5% of Relative Humidity.
- Storage area must be dry and clean.
- Keep the material in the original packaging when not used in order to protect it from dust and contamination.
- Do not expose to direct sunlight or heat sources.

All Ritrama products are subject to strict manufacturing controls to guarantee good quality products. The above information is based on research believed to be reliable, but does not constitute a warranty. All material should be tested by the purchaser to determine suitability of the product for their purposes. All information is subject to change without prior notice.

